



ANALYSIS OF CHEMICAL RESIDUES

Formaldehyde - as per Eco-Tex Standard 100

Limit Values: 20 ppm for Baby clothing, 75 ppm for textiles with skin contact, 300 ppm for other textiles

Tests in 1998

Growth	Test Date	Residue (ppm)
Chad	26.02.1998	n.d.
Mexico Juarez Acala	26.02.1998	n.d.
Sudan Acala	26.02.1998	1.0
USA El Paso 1517	26.02.1998	n.d.
USA Pima	26.02.1998	n.d.
Tests during 1992 to 1994		
Argentina	24.11.1992	0.0048
Chad	24.11.1992	0.0012
Giza-70	06.08.1993	n.d.
Giza-70	15.02.1994	n.d.
Israel-Pima	06.08.1993	n.d.
Peru-Pima	06.08.1993	n.d.
US Pima	06.08.1993	n.d.
Uzbekistan	24.11.1992	0.0004
n.d.: not detectable		